

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
17 July 2003 (17.07.2003)

PCT

(10) International Publication Number
WO 03/057705 A1

(51) International Patent Classification⁷: C07F 17/00

Casalecchio di Reno-Bologna (IT). **BALBONI, Davide**
[IT/IT]; Via Bastianino, 8, I-44100 Ferrara (IT).

(21) International Application Number: PCT/EP02/14899

(74) Agent: **COLUCCI, Giuseppe**; Basell Poliolefine Italia
S.p.a., Intellectual Property, P.le G. Donegani 12, I-44100
Ferrara (IT).

(22) International Filing Date:
30 December 2002 (30.12.2002)

(25) Filing Language: English

(81) Designated States (*national*): JP, US.

(26) Publication Language: English

(84) Designated States (*regional*): European patent (AT, BE,
BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT,
LU, MC, NL, PT, SE, SI, SK, TR).

(30) Priority Data:
02075040.2 8 January 2002 (08.01.2002) EP

Declaration under Rule 4.17:

— of inventorship (Rule 4.17(iv)) for US only

(71) Applicant (*for all designated States except US*): **BASELL
POLYOLEFINE GMBH** [DE/DE]; Brühler Strasse 60,
50389 Wesseling (DE).

Published:

— with international search report

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **RESCONI, Luigi**
[IT/IT]; Via Arianuova, 56/B, I-44100 Ferrara (IT).
GUIDOTTI, Simona [IT/IT]; Via Gaspari, 12, I-40033

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: PREPARATION OF SILICON-BRIDGED METALLOCENE COMPOUNDS

(57) ~~Abstract~~—A process for obtaining silicon-bridged metallocene compounds comprising the following steps: a) reacting, at a temperature of between 10° C and 70° C, the starting ligand with about 2 molar equivalents of an alkylating agent; b) after the reaction has been completed, adding at least 2 molar equivalents of an alkylating agent that can be also different from the first one; and c) reacting, at a temperature of between 10° C and 70° C, the product obtained from step b) with at least 1 molar equivalent of a compound of formula ML'_s, wherein M is a transition metal; s is an integer corresponding to the oxidation state of the metal; and L' is a halogen atom selected from chlorine, bromine and iodine.

WO 03/057705 A1